

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
S27	92	S26 and lateral and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S26	797	S24 and compress\$5 and tensi\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S24	160873	asahi.as.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S23	5060	S21 S22	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S22	1141	65/114,348,349.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S21	3951	428/409,410,426.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S14	57	S13 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S4	3664	428/409,410,426.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:41
S29	2	((("4508783") or ("3186815")).PN.	US-PGPUB; USPAT; JPO	OR	OFF	2006/08/01 14:44
S28	25	S27 and surface and peripheral\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 14:44
S30	14863	surface and peripheral\$3 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 15:55
S25	619	S24 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 15:55

EAST Search History

S31	560	S30 and temper\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 15:56
S32	327	S31 and central	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:00
S33	322	S32 not S28	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:01
S35	319	S33 not S34	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:04
S34	3	S33 and cracks and propagated	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:04
S37	129	S36 and residual	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:07
S36	258	S35 and stress	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:07
S38	143	S36 and glass	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 16:08
S39	87	S37 and glass	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:22
S53	87	S52 and glass	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S52	129	S51 and residual	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S51	258	S50 and stress	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23

EAST Search History

S50	319	S48 not S49	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S49	3	S48 and cracks and propagated	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S48	322	S47 not S44	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S47	327	S46 and central	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S46	560	S45 and temper\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S45	14863	surface and peripheral\$3 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S44	25	S43 and surface and peripheral\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S43	92	S42 and lateral and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S42	797	S41 and compress\$5 and tensi\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S41	160873	asahi.as.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S40	92	tempered adj glass and stress and residual and compress\$4 and tens\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 18:23
S54	73	S40 not (S53 S49 S44)	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 19:39

EAST Search History

S56	20	S55 not S54	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 19:40
S55	49	thickness and surface and tensi\$2 and compress\$4 and "tempered glass" and residual and average	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/01 19:40
S59	89	S57 S58	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 11:35
S58	9	yoda-kazushige.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 11:35
S57	85	kato-yasumasa.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 11:35
S1	77	kato-yasumasa.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 11:35
S60	9	S59 and glass and compress\$4	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 11:40
S79	20	S78 not S77	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S78	49	thickness and surface and tensi\$2 and compress\$4 and "tempered glass" and residual and average	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S77	73	S63 not (S76 S72 S67)	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S76	87	S75 and glass	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S75	129	S74 and residual	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15

EAST Search History

S74	258	S73 and stress	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S73	319	S71 not S72	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S72	3	S71 and cracks and propagated	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S71	322	S70 not S67	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S70	327	S69 and central	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S69	560	S68 and temper\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S68	14863	surface and peripheral\$3 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S67	25	S66 and surface and peripheral\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S66	92	S65 and lateral and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S65	797	S64 and compress\$5 and tensi\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S64	160873	asahi.as.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S63	92	tempered adj glass and stress and residual and compress\$4 and tens\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15

EAST Search History

S62	221	temper\$4 adj glass and stress and residual	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S61	80	S59 not S60	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 12:15
S11 4	199	S96 not (S95 S110 S106 S101 S113)	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S11 3	20	S112 not S111	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S11 2	49	thickness and surface and tensi\$2 and compress\$4 and "tempered glass" and residual and average	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S11 1	73	S97 not (S110 S106 S101)	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S11 0	87	S109 and glass	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 9	129	S108 and residual	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 8	258	S107 and stress	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 7	319	S105 not S106	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 6	3	S105 and cracks and propagated	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 5	322	S104 not S101	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57

EAST Search History

S10 4	327	S103 and central	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 3	560	S102 and temper\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 2	14863	surface and peripheral\$3 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 1	25	S100 and surface and peripheral\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S10 0	92	S99 and lateral and thickness	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S99	797	S98 and compress\$5 and tensi\$2	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S98	160873	asahi.as.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S97	92	tempered adj glass and stress and residual and compress\$4 and tens\$3	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S96	221	temper\$4 adj glass and stress and residual	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S95	89	S93 S94	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S94	9	yoda-kazushige.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S93	85	kato-yasumasa.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57

EAST Search History

S92	63	S91 and compress\$5 and tensile	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S91	231	S89 not S90	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S90	81	S89 and pattern	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S89	312	S88 and stress	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S88	899	S87 and temper\$4	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S87	164738	S86 not S85	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S86	164750	S83 S84	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S85	89	S81 S82	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S84	3951	428/409,410,426.ccls.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S83	160873	asahi.as.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S82	9	yoda-kazushige.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S81	85	kato-yasumasa.in.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57

EAST Search History

S80	199	S62 not (S59 S76 S72 S67 S79)	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:57
S11 5	184	S114 not S92	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	ON	2006/08/02 15:59